CALCOAST ANALYTICAL

Materials Chemistry

Certifled by

California Department of Health Services City of Los Angeles, Dept. of Building & Safety

March 12, 2003

Kel-Crete Industries, Inc. 1257 E. 29th St. Tulsa, OK 74114

Attn: Mr. Chuck Green

Ref: Lab File #0312-1A/03

1. SAMPLE(S):

One (1) gallon of Kel-Prime Bonding/Scaling/Curing Agent manufactured by Kellert Industries, P.O. Box 1830 Mannford, OK 74044

2. ANALYSIS PERFORMED:

Volatile Organic Compound (V.O.C.) Content per Bay Area Air Quality Management District/Regulations 8.

FAX ND. :5106523085

Mar. 12 2003 11:29AM P3

Page 2 of 2 Ref: Lab File #0312-1A/03

3. RESULTS:

Sample	Density (g/ml)	Lotal Volatile Content (‰w/w)	Total Water Content (%w/w)	γ.(g/litre),C.
Kel-Primc	1.031	62.66	60.39	62	0.52

Robert A. Haffner Chief Analytical Chemist

RAH:cc(3)

All samples submitted for testing will be held 30 days from report date at which time they will be returned to client or destroyed. Client will be responsible for all shipping, handling, and disposal charges. Samples will be stored upon written instructions and fee arrangements.

This report was made at the request of harder shouls only of the purchaser of said report. An angular of dissemination of information combined herein or materials of Calcost Labs. Inc., without prior written consental Calcoast Labs. Inc., is smidtly prohibited.